

EKOKAT RAPID ADH

Fast Setting Adhesive Mortar for Ceramics

DESCRIPTION

The product is a cement-based, fast hardening, high performance, and fast setting adhesive mortar with special chemical additives enhancing product performance, which is used for bonding of ceramic tiles, granite, marble, and natural stones.

It conforms to TS EN 12004 and C2F standards.

C2: Cement-based, High Performance Properties F: Fast Setting.

TECHNICAL SPECIFICATIONS

Appearance	Grey
Mixing Ratio	6-7 liters / 25 kg
Amount of Consumption	4-5 kg/m ²
Application Temperature	+5°C to +30°C
Rest Time under Exposed Conditions	15 minutes
Maturation Period	3 hours
Toxicity	Non-toxic
Splice Strength	> 1 N/mm ²
Slippage	≤ 0.5 mm
After immersed into water	≥ 1 N/mm ²
After thermally aged	≥ 1 N/mm ²
Temperature Resistance	- 40°C to + 80°C
Fire Reaction	A1
Time Before Availability For Traffic	24 hours

- * The above values are valid for + 23°C and 50% relative humidity. The time is shortened at high temperatures and extended at low temperatures.
- * If the temperature of the application surface is above +25 °C, then the surface should be moistened.

Date: 02.03.2017 Revision: 00

ÇULLAS YAPI MALZEMELERİ SANAYİ ve DIŞ TİCARET A.Ş.
Çoraklar Mahallesi 5024 Sokak No:10 Aliğa Organize Sanayi Bölgesi - Aliğa / İzmir
TURKEY
T. +90 216 457 80 10 F. +90 216 457 82 60
info@ekokat.com www.ekokat.com



EKOKAT RAPID ADH

Fast Setting Adhesive Mortar for Ceramics

AREAS OF USE

The product is used to apply ceramic, granite ceramic, granite, marble, and natural stone materials on concrete surfaces horizontally at interior and exterior spaces where fast application is needed. It is also used on balconies, terraces, and wet spaces.

BENEFITS

It is easy to prepare and apply. It sets fast. It has high adhesion strength. It is resistant to freeze-thaw cycling.

INSTRUCTIONS FOR USE

Care must be taken to ensure that the application surface is sound, dry, dust-free, and clean. Residues that will prevent adhesion on the surface should be cleaned. 25 kg of EKOKAT RAPID ADH is slowly poured into 6-7 liters of water and is then mixed with a low speed (400-600 rpm) mixer. The lump-free and homogenous mortar should be used in 10 minutes. The mortar should be notched with a notched trowel suitable for the tile dimensions. The mortar should not be used if its usage time has expired and it has been scabbed. The mortar should be applied at the specified application temperature, and protected from direct sun, wind and frost. Joint application can start three hours later.

PACKAGING

25 craft bags (PE reinforced)

64 shrink bags on one palette (110x110 cm).

STORAGE CONDITIONS AND SHELF LIFE

No more than two palettes should be placed on top of each other in their unopened original packaging, in a cool and dry environment. Shelf life is 12 months from date of production under suitable storage conditions.

SAFETY MEASURES

Work clothes, protective gloves, goggles, and masks suitable for workers health and safety should be used during the application. Due to irritant effects of uncured material, it should be washed with plenty of water and soap immediately in case of contact with skin and eyes. If swallowed, seek medical advice immediately. No food and drink should be brought into application areas. Store it out of reach of children. Please refer to the safety data sheet for further information.

RESPONSIBILITY

Our Company may not be held liable for any application errors that might be suffered if the product is not used for its intended purposes, or if it is failed to conform to the conditions and proposals specified above regarding technical application. This technical data sheet contains information that is current as of the date of issuance hereof. The manufacturer hereby reserves its right to change this data sheet at any time.

|||| EK 1005.010.25

 Grey

Date: 02.03.2017 Revision: 00

ÇULLAS YAPI MALZEMELERİ SANAYİ ve DIŞ TİCARET A.Ş.
Çoraklar Mahallesi 5024 Sokak No:10 Aliğa Organize Sanayi Bölgesi - Aliğa / İzmir
TURKEY
T. +90 216 457 80 10 F. +90 216 457 82 60
info@ekokat.com www.ekokat.com

